

STATIC SHIFT


Dissipative Force C0176

12 in x 12 in ESD Tile




| | |
|-----------------------------|----------------------------|
| Collection | Static Shift |
| Style | Dissipative Force (C0176) |
| Product Type | ESD Tile |
| Size | 12 in x 12 in |
| Construction | Homogeneous Resilient Tile |
| Total Thickness | 3 mm |
| Finish | Buff Finish |
| Installation | Glue Down |
| Recommended Adhesive | VPI 155 and VPI 165 |


Recommended Installation Methods




Brick Ashlar



Monolithic



Multi Directional



Quarter Turn




Vertical Ashlar

Colorways



On Mute
Color: 122



Take Five
Color: 525



New Normal
Color: 727



Circle Back
Color: 929



Night Watch
Color: 989

Testing

| | |
|---------------------------------|---|
| Classification | ASTM F1700 - Class I, Type A - Smooth |
| Squareness | ASTM F2055 - Passes - 0.010" max |
| Size and Tolerance | ASTM F2055 - Passes - ± 0.016 "/linear foot |
| Thickness | ASTM F386 - Passes - as specified ± 0.005 " |
| Flexibility | ASTM F137 - Passes - 1" mandrel |
| Dimensional Stability | ASTM F2199 - Passes - 0.020"/linear foot m |
| Resistance to Chemicals | ASTM F925 - Passes - No more than a slight change |
| Resistance to Light | ASTM F1515 - Passes, ?E = 8 |
| Resistance to Heat | ASTM F1514 - Passes, ?E = 8 |
| Radiant Flux | ASTM E648 - Class 1 (>0.45 W/cm ²) |
| Smoke Density | ASTM E662 - Passes both flaming and non-flaming - Less than 450 |
| Electrostatic Propensity | AATCC 134 - <30 V |

Sustainability

| | |
|------------------------------|--|
| Embodied Carbon | 10.4 kg CO ₂ e/m ² |
| Carbon Handprint | -10.92 kg CO ₂ e/m ² |
| Beyond Carbon Neutral | -0.52 kg CO ₂ e/m ² |
| EPD | Electrostatic Discharge Tile (ESD) |
| Country of Origin | USA |

Packaging

| | |
|-------------------------------|----|
| Square Feet Per Carton | 45 |
| Pieces Per Carton | 45 |
| Cartons Per Pallet | 36 |