

**STATIC SHIFT**


**Conductive Force C0177**

12 in x 12 in ESD Tile




<b>Collection</b>	Static Shift
<b>Style</b>	Conductive Force (C0177)
<b>Product Type</b>	ESD Tile
<b>Size</b>	12 in x 12 in
<b>Construction</b>	Homogeneous Resilient Tile
<b>Total Thickness</b>	3 mm
<b>Finish</b>	Buff Finish
<b>Installation</b>	Glue Down
<b>Recommended Adhesive</b>	VPI 155 and VPI 165


**Recommended Installation Methods**




Brick Ashlar




Monolithic



Multi Directional



Quarter Turn




Vertical Ashlar

**Colorways**



**On Mute**  
Color: 122



**Take Five**  
Color: 525



**New Normal**  
Color: 727



**Circle Back**  
Color: 929



**Night Watch**  
Color: 989

## Testing

---

<b>Classification</b>	ASTM F1700 - Class I, Type A - Smooth
<b>Squareness</b>	ASTM F2055 - Passes - 0.010" max
<b>Size and Tolerance</b>	ASTM F2055 - Passes - $\pm 0.016$ "/linear foot
<b>Thickness</b>	ASTM F386 - Passes - as specified $\pm 0.005$ "
<b>Flexibility</b>	ASTM F137 - Passes - 1" mandrel
<b>Dimensional Stability</b>	ASTM F2199 - Passes - 0.020"/linear foot m
<b>Resistance to Chemicals</b>	ASTM F925 - Passes - No more than a slight change
<b>Resistance to Light</b>	ASTM F1515 - Passes, ?E = 8
<b>Resistance to Heat</b>	ASTM F1514 - Passes, ?E = 8
<b>Radiant Flux</b>	ASTM E648 - Class 1 ( $>0.45$ W/cm <sup>2</sup> )
<b>Smoke Density</b>	ASTM E662 - Passes both flaming and non-flaming - Less than 450
<b>Electrostatic Propensity</b>	AATCC 134 - $<30$ V

## Sustainability

---

<b>Embodied Carbon</b>	10.4 kg CO <sub>2</sub> e/m <sup>2</sup>
<b>Carbon Handprint</b>	-10.92 kg CO <sub>2</sub> e/m <sup>2</sup>
<b>Beyond Carbon Neutral</b>	-0.52 kg CO <sub>2</sub> e/m <sup>2</sup>
<b>EPD</b>	Electrostatic Discharge Tile (ESD)
<b>Country of Origin</b>	USA

## Packaging

---

<b>Square Feet Per Carton</b>	45
<b>Pieces Per Carton</b>	45
<b>Cartons Per Pallet</b>	36